

Garish Crown Building Materials Ltd.

Technical Data Sheet

Power Neutral Cure Construction Sealant (Translucent)

Issuance date: 17/01/19

Revision date: -

Revision No.: 0

Product Specifications:

Physical Properties

Curing system:	Oxime
Appearance:	Paste
Color:	Translucent
Odor:	Slight unique odor
Density:	1.00 – 1.04 g/mL
Tack-free time:	10 – 30 minutes
Slump:	<1 mm
VOC content:	~43.7 g/L
Application temperature:	-20 °C to 50 °C
Service temperature:	-40 °C to 150 °C
Shelf life:	12 months
Packaging:	25 cartridges / carton

Cured Properties

Appearance:	Elastic rubber
Shore A Hardness:	20 - 35
Tensile at break:	≥1.0 MPa
Elongation at break:	≥300%

Product Description:

A one-component, high performance, 100% neutral cure silicone sealant formulated to give superior adhesion and durability in a wide range of glazing, weather sealing and trade applications. It has excellent resistance to weathering, UV radiation, vibration, moisture, ozone, temperature extremes, airborne pollutants, and many cleaning detergents and solvents.

Applications:

Well-suited for sealing metal lap joints in roofing, guttering and cladding applications. It will bond to form a strong weatherproof seal on most common building materials such as aluminium, galvanized and zinc-coated steel, painted surfaces, glass, brick, concrete and mirror bonding. It is suitable for both indoor and outdoor applications.

Directions:

1. Surfaces must be clean, dry and free of dirt, grease, oil or water.
2. Surfaces should be cleaned with alcohol, M.E.K. or other suitable solvent. Do not use soap or detergent.
3. For a neat finish, apply masking tape and remove it before sealant skins over.
4. Cut nozzle at 45° angle to desired bead-width and apply to substrate with cartridge gun.
5. Tool the sealant within 10 minutes of extrusion before it skins. Tack-free in 20 minutes.
6. Uncured sealant can be cleaned up with mineral spirits.

Features:

- 100% neutral cure silicone
- ASTM C920 (Class 25) compliant
- Excellent weathering resistance
- Permanently flexible
- Indoor and outdoor use

Clean up:

- Wet sealants can be cleaned up with acetone or mineral spirits.
- Cured sealants can only be removed mechanically.

Garish Crown Building Materials Ltd.

Technical Data Sheet

Power Neutral Cure Construction Sealant (Translucent)

Issuance date: 17/01/19

Revision date: -

Revision No.: 0

Limitations:

Not recommended for following applications:

- Structural glazing applications.
- Below waterline or permanent water immersion.
- Traffic areas subject to abrasion.
- Polycarbonate and polyacrylate, if under tension.
- Applications that requires the sealant to be painted.
- Neoprene rubber.

Joint Design:

- The specified sealant bead size should be calculated to comply with the compression and extension capabilities of the sealant in relation to the anticipated joint width due to expansion and contraction.
- Generally calculation of the width sealant bead should be computed on the basis of a maximum $\pm 25\%$ movement capability
- Minimum joint depth should not be less than 6 mm to accommodate movement.
- Sealant design joint width-to-depth ratio should be 2:1.

Curing Time:

Width	Depth	Coverage (300 ml) *
6 mm	6 mm	7.58 meter
10 mm	10 mm	2.73 meter
20 mm	10 mm	1.36 meter
25 mm	12 mm	0.91 meter

* The coverage figures shown above are approximate lineal meter run based on 10% wastage assumption. Actual coverage may vary.

- Calculation formula:

$$X / [(Y \times Z) \times 1.1] = \text{Coverage}$$

X = volume of cartridge (or sausage) in ml,

Y = joint width in cm, **Z** = joint depth in cm,

1.1 = 10% wastage assumption,

Coverage = lineal meter run in cm per cartridge (or sausage)

Caution:

Product releases methylethylketoxime during application and curing. May cause an allergic skin reaction. Avoid breathing vapours. Contaminated work clothing should not be allowed out of the workplace. Wear protective gloves. IF ON SKIN: Wash with soap and water. If skin irritation or a rash occurs: Get medical advice/attention. Wash contaminated clothing before reuse. Keep out of reach of children. Contains aminosilane. May produce an allergic reaction. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

Storage:

- Store in a dry and cool place with temperature below 30°C.
- Use within 12 months from date of production.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company will not accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.

- END -